

TECHNICAL SPECIFICATIONS:

DURABOARD®

Lifetime Exterior PVC Trim

I. CELUKA TYPICAL PROPERTIES(Based on 19 mm)

PROPERTY	TEST METHOD	UNIT	VALUE
PHYSICAL			
Specific Gravity	ASTM D 792	g/cm ³	0.50
Shore D Hardness	ASTM D 2240	D	65
MECHANICAL			
Flexural Strength @ Yield	ASTM D 790	psi	2,000
Flexural Modulus	ASTM D 790	psi	110,000
Dielectric Strength	ASTM D 149	kv/mm	12
THERMAL			
Heat Distortion Temperature	ASTM D 648	°F	130
Coefficient of Linear Expansion	ASTM D 696	in/in/°F	3.5 x 10 ⁻⁵
Thermal Conductivity	ASTM C 177	Btu in/hr ft ² °F	0.50

II. FLAMMABILITY STANDARDS

OTHER PROPERTY		RATING
UL 94	V0	Passed
UL 94	5V	Passed

III. AVAILABILITY

	STANDARD	CUSTOM
SIZE	4 ft x 8 ft (48" x 96")	Available upon request
COLOR	White	Available upon request
GAUGES (in millimeters)	6,10,13,16,19,25,30	Available upon request

The information contained herein is true and accurate to the best of our knowledge. All recommendations and suggestions are made without guarantees. This information is to be used by individuals with technical skill at their own discretion and risk. Because conditions of use are beyond our control, World-Pak Division, Intoplast Group, Ltd. makes no warranties, expressed or implied, and assumes no liability in connection with the use of this information.

Note: The above properties may vary slightly due to different sheet thickness.

07/07



Ply-Trim, Inc.
550 North Meridian Road
Youngstown, Ohio 44509
330-799-7876
1-800-PLY-TRIM